



中国认可
国际互认
检测
TESTING
CNAS L1978

国家建筑卫生陶瓷检测重点实验室
STATE KEY TESTING LABORATORY OF BUILDING CERAMICS AND SANITARY WARE
佛山海关综合技术中心
COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN CUSTOMS

TEST REPORT

Test report No.: **25202402683**

Page 1 of 2

Applicant: CHAOAN GUXIANG SHENGGE SANITARY WARES CO.,LTD.

Address of Applicant: Hengxi North Industry, Guxiang, Chaozhou City, Guangdong China

Name of Sample: Two Piece Toilet

Mark of Samples: 10001

Sizes of Sample: —

Source of Samples: Samples selected by applicant

Quantity of Samples: 1 Piece

Received on: 2024-07-09

Test Date: 2024-07-11~2024-07-17

Test Standard: AS 1976-1992
Vitreous china used in sanitary appliances

Results of Inspection: See Page 2

Stamp of inspection unit



Authorized Signatory

YUAN FANGLI

Date 2024-07-17

声明: 1、我们已尽所知所能实施上述检验, 不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务; 2、未经本实验室书面许可, 不得部分复制本报告; 3、本报告仅是样品的检测结果; 4、本报告所述的样品信息为委托单位自行声明, 实验室不负责其真实性。

Notes: 1. All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations.

2. This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 3. The results in this report apply to the samples only. 4. The product information are declared by applicant, and laboratory is not responsible for the authenticity.

广东省佛山市禅城区魁奇一路澜石(国际)金属交易中心十八座二楼 2/F, Building 18, Lanshi International Metal Exchange Center, Kuiqi Road, Chancheng District, Foshan, Guangdong, China 528000
Tel: 86-757-83960558 83827991 E-mail: fsiqtc@163.com

RZE-T1(2)

TEST REPORT

Test report No.: **25202402683**

Page 2 of 2

Test Item	Test Method	Test Result
Water absorption	AS 1976-1992 Appendix A	Individual values: 0.14%, 0.19%, 0.10% Arithmetic mean: 0.14%
Crazing	AS 1976-1992 Appendix B	None of the test specimens show any crazing
Chemical resistance	AS 1976-1992 Appendix C	Acetic acid, 10%: Unaffected Citric acid, 10%: Unaffected Hydrochloric acid(1:1) : Unaffected Sodium hydroxide, 5%: Unaffected Sodium stearate, 0.15%: Unaffected Sulfuric acid, 3%: Unaffected

*** **

End of Test Report



声明: 1、我们已尽所知所能实施上述检验, 不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务; 2、未经本实验室书面许可, 不得部分复制本报告; 3、本报告仅是样品的检测结果; 4、本报告所述的样品信息为委托单位自行声明, 实验室不负责其真实性。

Notes: 1. All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations.

2. This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 3. The results in this report apply to the samples only. 4. The product information are declared by applicant, and laboratory is not responsible for the authenticity.

广东省佛山市禅城区魁奇一路澜石(国际)金属交易中心十八座二楼 2/F, Building 18, Lanshi International Metal Exchange Center, Kuijiyi Road, Chancheng District, Foshan, Guangdong, China 528000
Tel: 86-757-83960558 83827991 E-mail: fsiqtc@163.com

DZE T10